
SPACTIVE® CT 3625

Characterization	Defoamer emulsion for water based coating systems
Chemical Structure	Emulsion based on organomodified polysiloxanes
Appearance	White emulsion
pH-Value	8.0+-1
Non volatile matter	25% +-1
Viscosity (25°C)	1000 - 2500 mPa*s
Stabilities	SPACTIVE® CT 3625 is sensitive to frost; after the impact of temperatures considerably below the freezing point irreversible changes could occur.
Storage	In closed original containers at room temperature (approx. 23°C) the product will be stable for at least 12 months. Stir before use.

The above given values are product describing data. Please consult the 'delivery specification' for binding product specifications. Further data about product properties, toxicological, ecological data as well as data relevant to safety can be found in the safety data sheet.

Properties

- Easy to incorporate
- Containing silica
- Free from mineral oils and APEO

Application Technique

Application Fields

SPACTIVE® CT 3625 is particularly characterised as defoamer for emulsion paints based on styrene acrylate copolymers, vinyl acetate copolymers and pure acrylates.

Preferred fields of application:

- Architectural paints
- Industrial coatings

Recommendation for Use

We generally recommend a dosage of 0.1 – 1.0 % calculated on the total formulation. The optimum dosage has to be determined through preliminary tests. The product can be added at any point of the production process.

We reserve the right to modify the product and technical leaflet.

Our department for applied technique is always at your service for further information and advice.

Our technical advice and recommendations given verbally, in writing or by trials are believed to be correct. They are neither binding with regard to possible rights of third parties nor do they exempt you from your task of examining the suitability of our products for the intended use. We cannot accept any responsibility for application and processing methods which are beyond our control.

Edition: January 2024

keim additec surface GmbH – a CHT Group Company

Postfach 12 04, 55478 Kirchberg / Hunsrück, Germany

Hugo-Wagener-Str. 9, 55481 Kirchberg / Hunsrück, Germany

Telephone: +49 6763/9333-0, Fax: +49 6763/9333-30, Email: info.kirchberg@cht.com,

www.keim-additec.de